

## FEATURES

: EPOGUARD ENAMEL is two-pack high gloss epoxy topcoat. It has excellent durability, adhesion, excellent chemical resistance and abrasion resistance.

As a finishing coat in epoxy system can be applied on steel and concrete surface, has excellent durability and adhesion property. It is a protective for steel structure, bridge, ship, factory floor, cagewash areas, chemical processing plants, warehouse, factory, food and beverage plants.

## TECHNICAL INFORMATION

Type	: Epoxy / Polyamide high gloss finish topcoat
Color	: White and other
Film appearance	: Gloss
Specific gravity	: 1.03 ± 0.05
Solid by volume	: 55 ± 2 %
Flash point	: 34 °C

		Minimum	Maximum	Recommended
Dry film thickness	(Microns)	50	60	50
Wet film thickness	(Microns)	91	109	91
Theoretical coverage.	m <sup>2</sup> / Liter	11.0	9.2	11.0
	m <sup>2</sup> / Gallon	41.6	34.7	41.6
Practical coverage.	m <sup>2</sup> / Liter	10.5	8.7	10.5
	m <sup>2</sup> / Gallon	40.0	33.0	40.0

Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

	25 °C	30 °C	35 °C	
Touch dry	Surface dry	4 hrs.	3 hrs.	2 hrs.
	Hard dry	10 hrs.	8 hrs.	6 hrs.
Recoat dry	Minimum	10 hrs.	8 hrs.	6 hrs.
	Maximum	-	-	-
Potlife	16 hrs.	12 hrs.	10 hrs.	

Remark : Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

## FILM PERFORMANCE

Properties	Test Method	Criteria	Results
Adhesion	ASTM D 3359	5B	Passed
Flexibility	ASTM D 522 (Method B)	3 mm	Passed
Impact Test	ASTM D 2794	60 inch-pounds	Passed
Abrasion Resistance	ASTM D 4060	200 mg (Loss)	Passed
	<small>CS-17 Wheels, 1000 g load, 1000 cycles</small>		
Chemical Resistance	ASTM D 1308	24 hrs.	Passed
Salt Spray Resistance	ASTM B 117	500 hrs.	Passed

## APPLICATION

Mixing Ratio	Part A	Part B
By Volume	4	1
By Weight	5	1

Application Method	Airless Spray	Air Spray	Brush / Roller
Diluted by <b>TOA Thinner 31</b>	5-10	15-20	10-15
Applicator	Graco 419	Coventional Spray (Iwata)	Short Hair Stiff Nylon Roller (Stanley)
	Graco 412		Stiff Nylon Brush
Pressure	50-180 kg/cm <sup>2</sup>	3-4 kg/cm <sup>2</sup>	-

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.

## APPLICATION SYSTEM

### Surface Preparation

#### Steel

: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project.

**Remark** : The surface must be thoroughly dry and apply the protective coating within 4 hours to cleaned surface.

#### Wall

: For New concrete - The concrete prior to laying plastic sheets to block moisture from underground. Then it should be left for curing concrete to solid and dry for about 3-4 weeks. Then, clean the surface free from dust, dirt, grease and most importantly, the surface is completely dry.

(Check moisture content must be less than 14%)

: For Old concrete - To remove the old paint film which loosely adhesion to as much as possible by Scraping with a shovel or Grinding machine to enhance adhesion. Then, clean the surface free from grease and oil with suitable solvent. Before primer coating should clean all surfaces free from dust, dirt, grease and most importantly, the surface is completely dry. (Check moisture content must be less than 14%).

#### Before Recoat by Topcoat

: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.

: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.

: Surface repair (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.

### Coating System

#### For Interior

##### Protective protective Coating

: Primer Rusttech 100 microns x 1 coat

: Topcoat **Epoguard Enamel** 50 microns x 2 coats

##### Concrete protective Coating

: Primer Epoguard Varnish 50 microns x 1 coat

: Topcoat **Epoguard Enamel** 50 microns x 2 coats

### Recommendation

: The proper relative humidity in the work shall not exceed 85% RH.

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

**HANDLING AND STORAGE****Storage condition**

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

**Shelf life**

: 24 months at 30-35 °C

**Package**

Packaging size	Part A :	Part B :
1 Gallon Set	1 Gallon	1/4 Gallon
5 Gallon Set	5 Gallon	1 Gallon

**HEALTH AND SAFETY**

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

**DISCLAIMER**

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

## คุณสมบัติ

: อีโพนาร์ค อินาเมล เป็นสีอีพ็อกซี่ 2 ส่วน คุณภาพสูง ให้ความเงางาม ปกป้องพื้นผิวดีเยี่ยม ใช้เป็นสีทับหน้าในงานปกป้องพื้นผิวที่ใช้ภายในอาคาร สำหรับพื้นผิวเหล็ก, ซีเมนต์, คอนกรีต และไม้ เช่นโครงสร้างเหล็กต่างๆ เครื่องจักร ผนังโรงงาน และภายในเรือ เป็นต้น ให้การปกป้องพื้นผิวจากสภาวะสิ่งแวดล้อมที่มีการกัดกร่อนของสารเคมี กรด-ด่าง น้ำมัน กนการขูดขีด ทำความสะอาดง่าย

## ข้อมูลทางเทคนิค

ประเภทของสี

สีทับหน้าชนิดอีพ็อกซี่ 2 ส่วน

เวดสี

ทาว , ตามที่ระบุใน Catalog

ลักษณะฟิล์มสี

เงา

ความถ่วงจำเพาะ

:  $1.03 \pm 0.05$ 

เนื้อสีโดยปริมาตร

55  $\pm$  2 %

จุดควบไฟ

34 องศาเซลเซียส

ความหนาฟิล์มสีเมื่อแห้ง

	ไม่น้อยกว่า	ไม่มากเกินไป	แนะนำ	
(ไมครอน)	50	60	50	
ความหนาฟิล์มสีเมื่อเปียก	91	109	91	
(ไมครอน)				
การครอบคลุมพื้นที่ (ทฤษฎี)	(ตร.ม. / ลิตร)	11.0	9.2	11.0
(ตร.ม. / แกลลอน)	41.6	34.7	41.6	
การครอบคลุมพื้นที่ (ปฏิบัติ)	(ตร.ม. / ลิตร)	10.5	8.7	10.5
(ตร.ม. / แกลลอน)	40.0	33.0	40.0	

หมายเหตุ : การผสม,การใช้งาน,ความหยาบและรูพรุนของพื้นผิว มีผลต่อการปกคลุมพื้นผิว

ระยะเวลาแห้งสัมผัส

อุณหภูมิ	25 °C	30 °C	35 °C
แห้งผิว	4 ชั่วโมง	3 ชั่วโมง	2 ชั่วโมง
แห้งแข็ง	10 ชั่วโมง	8 ชั่วโมง	6 ชั่วโมง
ระยะเวลาแห้งทาทับ	อย่างน้อย	8 ชั่วโมง	6 ชั่วโมง
ระยะเวลาแห้งสมบูรณ์	อย่างมาก	-	-
อายุการใช้งานหลังผสม	16 ชั่วโมง	12 ชั่วโมง	10 ชั่วโมง

ระยะเวลาแห้งทาทับ

ระยะเวลาแห้งสมบูรณ์

อายุการใช้งานหลังผสม

หมายเหตุ : การระบายอากาศ อุณหภูมิ ความหนาของฟิล์มสี และจำนวนชั้นของฟิล์มสี จะมีผลกระทบต่อและสัมพันธ์กับระยะเวลาในการแห้งของฟิล์มสี

## คุณสมบัติของฟิล์มสี

Properties	Test Method	Criteria	Results
การยึดเกาะ	ASTM D 3359	5B	ผ่าน
ความยืดหยุ่น	ASTM D 522 (Method B)	3 มม.	ผ่าน
ความทนต่อการกระแทก	ASTM D 2794	60 นิ้ว-ปอนด์	ผ่าน
การทนต่อรอยขูดขีด	ASTM D 4060	200 มก. (ที่หายไป)	ผ่าน
	สื่อ CS17, น้ำหนักบรรทุก 1000 กรัม, 1000 รอบ		
การทนต่อสารเคมี	ASTM D 1308	24 ชั่วโมง	ผ่าน

## วิธีใช้งาน

อัตราส่วนผสม	ส่วน เอ	ส่วน บี
โดยปริมาตร	4	1
โดยน้ำหนัก	5	1



**ข้อมูลสุขภาพและความปลอดภัย**

- : กรุณาดูข้อควรระวังที่ติดไว้หน้ากระป๋อง การทำงานสีควรทำในที่ที่อากาศถ่ายเทได้สะดวก อย่าสูดหายใจเอาละอองสีเข้าไปโดยตรง ควรใส่หน้ากากเมื่อทำการพ่นสี และพยายามเลี่ยงมิให้สัมผัสผิวหนังโดยตรง ถ้าสัมผัสผิวหนังควรล้างด้วยน้ำสะอาด และสบู่ทันที หากกระเด็นเข้าตาควรล้างด้วยน้ำสะอาดทันที แล้วรีบไปพบแพทย์
- : รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในเอกสารข้อมูลความปลอดภัย (SDS)

**การสงวนสิทธิ์เรียกร้อง**

- : รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในภาวะที่ต่างกัน เราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น
- : บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมีต้องแจ้งล่วงหน้า